

CURING: Care should be taken to protect Aqua Pearl from rapid drying conditions such as high wind, high temperature, low humidity. Such precautions may include fogging or misting the surface or placing a protective covering over the pool. Cover should not be placed directly on pool surface.

FILLING PROCEDURES: When filling a pool it is important to do so without interruption of fill water. Fill pool as rapidly as possible. All fill hoses should have a sock or cloth on the end. Do not allow main hose length to lay on the plaster surface, as it will leave a mark.

WATER CHEMISTRY: The pool water must be carefully balanced from the initial fill and constantly maintained within NSPI recommended guidelines. Maintaining proper chemical balance from first fill is essential to maximize the life of the pool surface. Please consult your MAGIC TECHNOLOGIES Product Service Representative concerning start-up techniques and maintenance programs.

COVERAGE: Each 80 lb bag of Aqua Pearl covers approximately 12 - 15 sq. ft. per bag on "NEW" construction and 13 - 17 sq. ft. per bag on "RENOVATION" at 3/8" to 1/2" thickness. Coverage rates may vary depending on method of application and condition of substrate.

PACKAGING: Aqua Pearl is packaged in 80-lb. heavy-duty poly-lined bags.

WARNINGS: Product is alkaline on contact with water. During mixing or application, avoid contact with eyes or skin. In case of such contact, flood eyes repeatedly with water and call physician. Do not take internally. Wear NIOSH approved mask during mixing procedures.